

DATASHEET

1P13 TUFNOL

1P13 Tufnol is a low-cost commercial paper-based laminate, produced to meet the need for an economical material where electrical requirements are moderate. As a good basic, low voltage insulation material, this grade has a higher mechanical strength than the other phenolic paper grades and a greater impact strength.

Applications

- Engineering Parts
- Spacers
- Base Plates
- Jigs & Fixtures

Availability

- Colour Natural
- Type Sheet, Rod & Tube
- Regularly produced in a wide variety of thicknesses

Typical Properties

| Property | Units | Result |
|--|-------|---------|
| Cross Breaking Strength | MPa | 175 |
| Impact Strength, Notched, Charpy | kJ/m2 | 3.9 |
| Shear Strength, Flatwise | MPa | 100 |
| Tensile Strength | MPa | 164 |
| Young's Modulus | GPa | 10.4 |
| Water Absorption: | | |
| - 1.6mm thick | mg | 65 |
| - 3mm thick | mg | 80 |
| - 6mm thick | mg | 100 |
| - 12mm thick | mg | 150 |
| Electric Strength, Flatwise in Oil at 90°C: | | |
| - 1.6mm thick | MV/m | 10 |
| - 3mm thick | MV/m | 6.2 |
| - 6mm thick | MV/m | 4.0 |
| Electrical Strength, Edgewise in Oil at 90°C | kV | 25 |
| Insulation Resistance after Immersion in Water | ohms | 5x108 |
| Relative Density | - | 1.36 |
| Maximum Working Temperature: | | |
| - Continuous | C° | 90 |
| - Intermittent | °C | 120 |
| Thermal Classification | - | Class E |